

HPMC

(Hydroxypropyl methyl cellulose)

Technical data sheet of HPMC

Items	Specification		
Content of Methoxy %	28.0-30.0	27.0-30.0	19.0-24.0
Content of Hydroxypropyl %	7.0-12.0	4.0-7.5	4.0-12.0
Temperature of Gelatin °C	58-64	62-68	70-90
Moisture Content (wt %)	≤5		
Ash (wt %)	≤1.0		
PH value	4.0-8.0		
Appearance	White or Off-White Powder		
Fineness ,mesh	>80 Meshes		
Transmittance of light	≥90		
Viscosity(mpa.s)	50-200000(It can be customized)		

